

## TECHNICAL DATA SHEET

### ----- FAÇADE DIVISION -----

#### Blankor

#### **sez. 1.0 Technical characteristic**

BLANKOR is a special pigmented, infilling, primer for exteriors. It consists of acrylic resins in water dispersion and titanium dioxide fillers. The product is highly pervasive, consolidates the surface and makes the absorption uniform. Thanks to its excellent hiding power, it allows saving on finishing products. BLANKOR can be applied on alkaline substrates, civil plasters, rough plasters, old walls, chalking or highly absorbent plasters. It has a low odour level, is, noninflammable and friendly to both humans and the environment.

#### **sez. 2.0 Ideal Use**

Internal and external walls.

#### **sez. 3.0 Surface preparation**

The surface to be treated must be thoroughly dry and mature. New plasters need at least 30 days for maturation and to allow complete carbonation of the support. Sand down or strip surfaces in order to remove imperfections and any loose or flaking materials. On restoration projects, leaks and water infiltrations must be completely repaired.

#### **sez. 4.0 Application method**

Apply one coat of BLANKOR by OIKOS diluted with 50 ÷ 80% drinkable water by using a brush, roller or spray gun (1.7 mm nozzle). Allow 6 ÷ 8 hours to dry before the application of finish products.

#### **sez. 5.0 Finish**

Finish products from the Façade Division

#### **sez. 6.0 Technical Characteristic: application**

Dilution	Dilute with 50 ÷ 80% drinkable water
Yield	14 ÷ 18 m <sup>2</sup> /lt in one coat approx. depending on the substrate absorption
Application tools	Brush, roller or spray gun (1.7 mm nozzle)
Application temperature	+5°C ÷ +36°C (with relative humidity not higher than 80%)
Drying time: tack free	1 ÷ 2 hours (temperature = +20°C with relative humidity not exceeding 75%)
Drying time: fully cured	10 ÷ 12 hours (temperature = +20°C with relative humidity not exceeding 75%)
Drying time: painting over	6÷8 hours (temperature = 20°C with 75% relative humidity)
Tools cleaning	Water

#### **sez. 7.0 Technical Characteristic: the product**

Composition	Acrylic resins in water dispersion, high coverage fillers, titanium dioxide, organic and inorganic pigments and preservatives to aid application and the formation of the surface film..
Specific weight	1.37 kg/l +/-3% (White)
pH	8 ÷ 9
Viscosity	20,500 +/-5% CPS Brookfield (RVT 20 revs/min. a 25°C)
Storage temperature	+2°C ÷ +36°C. Keep from freezing.
Reaction to fire	None if applied on to non-inflammable surfaces: water-based material with dry thickness less than 0.600 mm
Resistance to tear and adhesion	In compliance with DIN ISO 4624 standard: tear resistance 1.3 N/mm <sup>2</sup> , cohesion crack under the paint working range
Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE	Classification: A/h; VOC: 20 g/l (max); Limit Phase I (from 01/01/2007): 50g/lt, Limit Phase II (from 01/01/ 2010): 30g/lt

Available colours	White + colours chart by the tinting machine DCS Décor Color System by OIKOS
Packaging	4 – 14 l

### sez 8.0 Toxicological data

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is considered to be a non dangerous substance if used in the technically correct manner. Normal cautionary measures for the handling of water based paints are advised. No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements

### sez. 9.0 Specifications

Clean the surfaces to be decorated and remove any loose or flaking material. In case of new plasters, make sure the substrate is thoroughly dry. Apply one coat of a fixing and filling agent such as BLANKOR by OIKOS. Allow 6 ÷ 8 hours to dry before proceeding in the application of finish products. All procedure must be carried out following closely all application instructions, cost ..... per m<sup>2</sup> including application and materials. Scaffolding not included.

### Note

*The company Oikos S.r.l guarantees, to the best of its own technical and scientific knowledge, that the information contained in this technical data sheet is correct. Notwithstanding that indicated above, Oikos takes no responsibility for the results obtained through the use of this product in as much as it is not possible for Oikos to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put*